

Toroids (5967003801)



Part Number: 5967003801

67 TOROID

Explanation of Part Numbers:

- Digits 1&2 = product class
- 3&4 = material grade
- 9th digit 1 = Parylene coating
- 2 = thermo- set plastic coating

A ring configuration provides the ultimate utilization of the intrinsic ferrite material properties. Toroidal cores are used in a wide variety of applications such as power input filters, ground- fault interrupters, common- mode filters and in pulse and broadband transformers.

- All toroidal cores are supplied burnished to break sharp edges.
- For any toroidal core requirement not listed in the catalog, please contact our customer service department for availability and pricing.

Coating Options:

- Toroids with an outside diameter of 9.5 mm (0.375") or smaller can be supplied Parylene C coated. The Parylene coating will increase the "A" and "C" dimensions and decrease the "B" dimension a maximum of 0.038 mm (0.0015"). The ninth digit of a Parylene coated toroid part number is a "1". See reference tables for the material characteristics of Parylene C. Parylene C coating is RoHS compliant.
- Toroids with an outside diameter of 9.5 mm (0.375") or larger can be supplied with a uniform coating of thermo- set plastic coating. This coating will increase the "A" and "C" dimensions and decrease the "B" dimension a maximum of 0.5 mm (0.020"). The 9th digit of the thermo- set plastic coated toroid part number is a "2". Thermo- set plastic coating is RoHS compliant.
- Thermo- set plastic coated parts can withstand a minimum breakdown voltage of 1000 Vrms, uniformly applied across the "C" dimension of the toroid.

The $\square C \square$ dimension may be modified to suit specific applications.

Weight: 106 (g)

Dim	mm	mm tol	nominal inch	inch misc.
A	61	±1.30	2.4	—
B	35.55	±0.85	1.4	—
C	12.7	±0.50	0.5	—

Chart Legend

$\Sigma l / A$: Core Constant, Effective Core Volume
 l_e : Effective Path Length,
 A_e : Effective Cross- Sectional Area, V_e :
 A_L : Inductance Factor

Electrical Properties	
A_L (nH)	55 +35%, -25%
A_e (cm ²)	1.58
$\Sigma l / A$ (cm ⁻¹)	9.2
l_e (cm)	14.5
V_e (cm ³)	22.8

Toroids are tested for A_L values at 10 kHz.

Fair- Rite Products Corp. • One Commercial Row, Wallkill, New York 12589-0288
888-324-7748 • 845-895-2055 • Fax: 845-895-2629 • ferrites@fair-rite.com • www.fair-rite.com